

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
16 May 2002 (16.05.2002)

PCT

(10) International Publication Number
WO 02/39533 A2

- (51) International Patent Classification⁷: H01M 8/10
- (21) International Application Number: PCT/EP01/13135
- (22) International Filing Date:
8 November 2001 (08.11.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/248,076 9 November 2000 (09.11.2000) US
- (71) Applicant: IRD A/S [DK/DK]; Kullinggade 31, DK-5700 Svendborg (DK).
- (72) Inventors: ODGAARD, Madeleine; Ahlefeldtsvej 14, DK-5230 Odense (DK). YDE-ANDERSEN, Steen; Sankt Nikolai Kirkest Æde 2A, DK-5700 Svendborg (DK).
- (74) Agents: ABLETT, Graham, Keith et al.; Ablett & Stebbing, Caparo House, 101-103 Baker Street, London W1U 6FQ (GB).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: MEMBRANE ELECTRODE ASSEMBLIES FOR DIRECT METHANOL FUEL CELLS AND METHODS FOR THEIR PRODUCTION



(57) Abstract: A method of producing a membrane electrode assembly (1) for use in direct methanol fuel cells by serigraphically printing cathode catalysts (3) or anode catalysts (6) with a carbon baking layer (4, 7) onto graphite or carbon paper (5, 8), boiling impurities from these layers, and bonding the boiled, printed cathode and anode catalyst layers onto opposite sides of a polymer electrolyte membrane (2) via semi-isostatic compression in a constraint which restricts volume and lateral deformation is provided. Also provided are membrane electrode assemblies produced in accordance with this method.

Membrane Electrode Assemblies for Direct Methanol Fuel
Cells and Methods for their Production

Field of the Invention

5 The present invention relates to membrane
electrode assemblies for use in direct methanol fuel cells.
The membrane electrode assemblies of the present invention
comprise a polymer electrolyte membrane with cathode and
anode layers having a low content of catalysts with cathode
10 and anode layers on either side of the membrane. The
membrane electrode assemblies are serigraphically printed
on an electron conducting substrate such as graphite or
carbon paper with an ink comprising catalyst loaded carbon
and water dispersed polymer electrolyte membrane material
15 dispersed in a mixture of water, propanol and methanol.
Following printing, the anode and cathode layers are boiled
in deionized water to remove impurities. The anode and
cathode layers and the polymer electrolyte membrane are
then placed in a constraint and axially or semi-
20 isostatically compressed, preferably via heat, to form the
membrane electrode assemblies.

Background of the Invention

Fuel cells are energy conversion devices being
25 considered as a possible alternative to internal combustion
engines. One type of fuel cell comprises a solid polymer
electrolyte (SPE) membrane, such as a sulfonated
fluorinated polymer membrane material like NAFION, which
provides ion exchange between the cathode and anode
30 electrodes. Various configurations of SPE fuel cells as
well as methods for their preparation have been described.
See e.g. U.S. Patent 4,469,579; U.S. Patent 4,826,554; U.S.
Patent 5,211,984; U.S. Patent 5,272,017; U.S. Patent
5,316,871; U.S. Patent 5,399,184; U.S. Patent 5,472,799;

U.S. Patent 5,474,857; and U.S. Patent 5,702,755.

SPE fuel cells offer several advantages over liquid electrolyte fuel cells. These include greater power densities, lower operating temperatures, and longer
5 operating lifetimes. In addition, SPE materials are generally resistant to corrosion and easy to incorporate into fuel cell structures. Accordingly, attempts have been made to utilize these various solid polymer electrolyte (SPE) fuel cells as an electronic power source for electric
10 automobiles and space crafts.

However, the need for a catalyst such as platinum in the SPE fuel cells has made these cells more expensive than alternative energy sources.

The present invention provides a method for
15 producing SPE fuel cells with lower catalyst content and enhanced electrochemical efficiency.

Summary of the Invention

An object of the present invention is to provide a
20 method for producing membrane electrode assemblies for use in direct methanol fuel cells which comprises serigraphically printing cathode and anode catalyst layers onto graphite or carbon paper; boiling the printed cathode and anode layers to remove impurities; placing a polymer
25 electrolyte membrane between the cathode and anode layers and inserting them into a constraint which restricts their volume and lateral defamation; and semi-isostatically compressing the cathode and anode layers to the polymer electrolyte membrane.

30 Another object of the present invention is to provide a more electrochemically efficient membrane electrode assembly comprising a polymer electrolyte membrane and printed anode and cathode layer comprising a low content of catalysts located on either side of the
35 polymer electrolyte membrane, wherein the printed anode and

- 3 -

cathode layers were washed to remove impurities prior to assembly.

Brief Description of the Drawings

5 Figure 1 provides a side view of a membrane electrode assembly of the present invention including the polymer electrolyte membrane as well as the washed anode and cathode layers on the carbon or graphite paper.

10 Figure 2 provides a side view of a membrane electrode assembly within an aluminum foil constraint following semi-isostatic compression.

Detailed Description of the Invention

 The present invention relates to membrane
15 electrode assemblies with increased electrochemical efficiency and methods for producing these assemblies for use in direct methanol fuel cells. A membrane electrode assembly of the present invention is depicted in Figure 1. As shown in Figure 1, the membrane electrode assembly 1
20 comprises a polymer electrolyte membrane (PEM) 2. As also shown in Figure 1, a cathode catalyst 3 and porous carbon backing layer 4, which are applied preferably via serigraphic printing to a graphite or carbon paper 5, are attached to one side of the polymer electrode membrane 2 so
25 that the cathode catalyst 3 is adjacent to the polymer electrolyte membrane 2. An anode catalyst 6 and porous carbon backing layer 7, which are applied preferably via serigraphic printing to a graphite or carbon paper 8, are attached to the opposite side of the polymer electrode
30 membrane 2. The cathode catalyst 3 comprises conductive carbon black loaded with a catalyst. This layer 3 is cast with a homogenous ink comprising carbon black supported platinum catalyst and polytetrafluoroethylene (PTFE) uniformly dispersed in a solution of ionomer. PTFE is

- 4 -

included in the cathode catalyst layer 3 at a wt% sufficient to render the cathode catalyst material hydrophobic in nature on the oxygen side and to fill the free percolation volume of the contacting particles so that porosity is significantly minimized. The concentration of PTFE in the cathode catalyst 3 is from 5 to 42 wt% with the concentration range of 25 to 32 wt% being preferred. The anode catalyst 6 is cast using a homogenous ink composition prepared from a soluble form of the ionomer, conductive carbon black supported platinum, a noble metals such as Ru, Rd, Pd, Re, Os or Ir and PTFE. The anode catalyst 6 comprises less PTFE as compared to the cathode catalyst 3. PTFE concentrations range from 5 to 20 wt% with 7 wt% being preferred. The porous carbon backing layers 4 and 7 are comprised of carbon black and a polymer electrolyte material. The carbon backing layers are cast between the cathode catalyst layer 3 or anode catalyst layer 6 and porous graphitized paper layers 5 and 8 using a homogenous ink containing conductive carbon black particles, dispersed ionomer and polytetrafluoroethylene. Following application of each cathodic and anodic layer to the graphite or carbon paper, they are boiled for several hours to remove impurities.

The complete assembly with both the washed cathodic layers and washed anodic layers of the electrode structure in place is then simultaneously bonded to the wet polymer electrolyte membrane by semi-isostatic compression in a constrain which restricts volume and lateral defamiation of the materials. In a preferred embodiment, heat compression is used at a temperature ranging between 120° and 180°C, preferably 135°C to 169°C, more preferably 140°C, and a surface pressure of 10 to 150 bar, preferably 10 to 40 bar, more preferably 20 bar. A preferred constraint for use in this compression comprises an

- 5 -

aluminum foil envelope sealed via a hot melt adhesive and line with Teflon sheeting to provide for lateral accommodation of the membrane electrode assembly.

In contrast to prior art procedures, to produce the assembly of the present invention, the cathode and anode catalyst layers are applied, preferably via serigraphic printing, to the porous graphite or carbon paper and not to the polymer electrolyte membrane, thus reversing the usual procedure for assembly. Accordingly, this method of production eases assembly as it ensures intimate contact and adherence of the catalyst layer to the polymer electrolyte membrane. Further, the method of present invention provides a more logical sequencing in that the layer requiring highest compaction is positioned to be in direct contact with the polymer electrolyte membrane. Thus, application of heat and pressure ensure good adhesion and cohesion of the catalyst layers while avoiding subsequent loss of contact and delamination on thermal cycling. The carbon and backing layer as well as the carbon or graphite paper provide for optimal gas permeability.

Further, after application of each layer, the cathode and anode layers are boiled for several hours to remove impurities. Each layer is dried before the next layer is printed and superimposed. Preferred boiling and drying conditions for the layers are described in the following examples.

Membrane electrode assemblies prepared in accordance with the method of the present invention have been demonstrated to have increased electrochemical efficiency as compared to standard membrane electrode assemblies. Specifically, fuel cells with the new membrane assemblies exhibited higher cell voltage at the same current density as fuels cells prepared in accordance with standard methods. Accordingly, the membrane electrodes

assemblies of the present invention provide more efficient fuel cells for use in transportation and other areas.

The following nonlimiting examples are provided to further illustrate the present invention.

5 EXAMPLES

Example 1: Preparation of Anode Catalyst Layer Ink

Water and glycerine are added to the anode catalyst (60 wt% Pt-Ru mixed with added carbon (C) to weight ratios of 1:2 for catalyst and water and 1:4 for
10 water and glycerine). The solid content or dry matter contained in the liquid dispersion is between 1 and 6 vol%. The mixture is homogenized and dispersed using an Ultra Turrax micronizing attritor at 8000 RPM for 15 minutes.

A solubilized perfluorosulfonate ionomer such as
15 NAFION (E.I. duPont, Fayetteville, NC) in 5 wt% solid content propanol solution is available from Solution Technology, Inc. (Mendenhall, PA). A catalyst composition having a metal to dry NAFION ratio of 95.5 wt% Pt/Ru:7.5 wt% dry NAFION is then added. This mixture is then homogenized and
20 dispersed using an Ultra Turrax micronizing attritor at 8000 RPM for 15 minutes.

To obtain proper ink viscosity suitable for screen printing, 50 vol% of the mixed suspension dispersion media is then removed by evaporation upon stirring when the
25 greater part of the low molecular weight volatile solvents and contaminants are removed. The material is then dispersed using an Ultra Turrax micronizing attritor at 8000 RPM.

Example 2: Preparation of Anode Carbon Layer

30 Water and glycerine are added to conductive carbon black in weight ratios of 5:7:35 for carbon:water:glycerol. A solubilized perfluorosulfonate ionomer such as NAFION in 5% solution in weight percent of 7.5:92.5 for NAFION(dry):C is then added. The components are then mixed by
35 micronizing attrition with an Ultra-Turrax attritor for at

least 10 minutes at 8000 RPM in order to completely disperse the carbon black in the ionomeric base.

Example 3: Preparation of Anode Carbon Paper

Carbon paper (Toray Inc. Supplied by E-TEK, Inc. Natick, MA) is impregnated by immersion in a dispersion of polytetrafluoroethylene (PTFE). In one embodiment, a diluted 60% PTFE emulsion is used. Typically, a suspension contains 1-20 wt% of the PTFE in water. In this example 5 wt% of PTFE dispersed in water is used. The impregnated carbon paper is dried at 90°C for approximately 12 hours and finally sintered at 370°C for 20 minutes.

Example 4: Printing

The anode carbon layer is screen printed onto the hydrophobic carbon paper with a total loading of approximately 2 mg C-NAFION/cm². This is obtained via a sequence of repeated printing operations until the required loading is printed on the paper. One layer is printed at a time followed by thermal drying and consolidation treatment comprising a first step at 40°C for 15 minutes and a second step at 100°C under vacuum for 20 minutes. The open porous assembly of carbon structure and the superimposed carbon layer thus obtained is then boiled in deionized water for 1 hour. Typically 2 steps are required to remove residual solvents and contaminants and attain a loading of 2 mg/cm².

The anode catalyst layer is then printed onto the carbon layer. One application is performed followed by curing which comprises a first step at 40°C for 15 minutes followed by a second step at 100°C under vacuum for 20 minutes. Multiple applications are added until the desired catalyst loading, preferably ≤ 1.0 mg PtRu/cm², is attained in the anode catalyst layer.

The resulting porous anode structure is then boiled in deionized water for at least 1-2 hours in order to completely remove volatile contaminants and solvents.

Example 5: Preparation of Cathode Catalyst Layer Ink

Water and glycerine are added to the cathode catalyst (60 wt% Pt/C) to weight ratios of 1:2 for catalyst:water and 1:4 for water:glycerine. A solubilized perfluorosulfonate ionomer such as NAFION in 5% solution is added in an amount so that the cured electrode is composed of 25 wt% of the ionomer. Polytetrafluoroethylene in a 60% dispersion to weight ratios depending on the supported catalyst composition used is then added. For example, 30-40 wt% PTFE is used for 20 wt% Pt-C; 10-20 wt% PTFE is used for 60 wt% Pt-C.

The components are thoroughly mixed by attrition as described in Example 1 for at least 10 minutes to uniformly disperse the supported cathode catalyst material.

To obtain proper ink viscosity suitable for screen printing, 50 vol% of the mixed suspension dispersion media is then removed by evaporation upon stirring and finally mixed using an Ultra Turrax micronizing attritor at 8000 RPM.

Example 6: Preparation of Cathode Carbon Layer Ink

Water and glycerine were added to carbon black in weight ratios of 1:1:4 for carbon:water:glycerine. Solubilized perfluorosulfonate ionomer such as NAFION in 5% solution and polytetrafluoroethylene (PTFE) in a 60% dispersion in wt% of 25:10:65 for NAFION(dry):PTFE:C was added. The components were mixed by mechanical stirring for at least 10 minutes to disperse the carbon black in the ionomer.

Example 7: Preparation of Hydrophobic Cathode Carbon

Paper Carbon paper (Toray Inc. Supplied by E-TEK, Inc. Natick, MA) is impregnated by immersion in a dispersion of polytetrafluoroethylene. In one embodiment, a diluted 60% PTFE emulsion is used. Typically, a suspension contains 20 wt% of the PTFE in water. The impregnated carbon paper is dried at 90°C for approximately 12 hours and finally

sintered at 370°C for 20 minutes.

Example 8: Printing

The cathode carbon layer is applied onto the wet proofed carbon paper with loading of typically 2 mg/cm² by
5 screen printing in the same manner as described for the anode layer in Example 4. One layer is printed at a time followed by thermal treatment consisting of a first step at 40°C for 15 minutes and a second step at 100°C under vacuum for 20 minutes. The resulting porous structure is then
10 boiled in deionized water for 1 hour.

The cathode catalyst layer is then printed onto the carbon layer. One layer is printed at a time followed by a curing which comprises a first step at 40°C for 15 minutes and a second step at 100°C under vacuum for 20
15 minutes. The resulting porous cathode structure is again boiled in deionized water for 1 hour.

Example 9: Bonding of Electrode Structures

The anode and cathode structures are then hot
20 pressed at 140°C for 4 minutes and a specific surface pressure of 10 to 150 kg/cm² to a solid polymer membrane such as NAFION 117 which has been previously equilibrate in water for 24 hours before use. Preferably 20 kg/cm² surface specific pressure is used. No hydraulic line pressure is
25 used.

- 10 -

What is Claimed is:

1. A method of producing a membrane electrode assembly for use in direct methanol fuel cells comprising:
 - (a) serigraphically printing a cathode carbon backing layer onto graphite or carbon paper;
 - (b) boiling the printed cathode carbon backing layer and graphite or carbon paper;
 - (c) serigraphically printing a carbon cathode catalyst onto the boiled, printed carbon backing layer and graphite or carbon paper to produce a cathode layer;
 - (d) boiling the cathode layer;
 - (e) serigraphically printing an anode carbon backing layer on graphite or carbon papers;
 - (f) boiling the printed anode carbon backing layer and graphite or carbon paper;
 - (g) serigraphically printing a carbon anode catalyst onto the boiled, printed anode carbon backing layer and graphite or carbon paper to produce an anode layer;
 - (h) boiling the anode layer;
 - (I) inserting a polymer electrolyte membrane between the boiled cathode layer and boiled anode layer and placing the membrane and cathode and anode layers into a constraint which restricts volume and lateral defamation;
 - (j) semi-isostatically compressing the membrane and cathode and anode layers into a membrane electrode assembly.
2. A membrane electrode assembly for use in direct methanol fuel cells produced in accordance with the method of claim 1.

1/1




FIG. 1




FIG. 2

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
16 May 2002 (16.05.2002)

PCT

(10) International Publication Number
WO 02/039533 A3

(51) International Patent Classification⁷: **H01M 8/10**

(21) International Application Number: PCT/EP01/13135

(22) International Filing Date:
8 November 2001 (08.11.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/248,076 9 November 2000 (09.11.2000) US

(71) Applicant: IRD A/S [DK/DK]; Kullinggade 31, DK-5700
Svendborg (DK).

(72) Inventors: ODGAARD, Madeleine; Ahlefeldtsvej 14,
DK-5230 Odense (DK). YDE-ANDERSEN, Steen; Sankt
Nikolai Kirkest Æde 2A, DK-5700 Svendborg (DK).

(74) Agents: ABLETT, Graham, Keith et al.; Ablett & Steb-
bing, Caparo House, 101-103 Baker Street, London W1U
6FQ (GB).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,

CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU,
ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD,
TG).


Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(88) Date of publication of the international search report:
27 February 2003

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: MEMBRANE ELECTRODE ASSEMBLIES FOR DIRECT METHANOL FUEL CELLS AND METHODS FOR
THEIR PRODUCTION



(57) Abstract: A method of producing a membrane electrode assembly (1) for use in direct methanol fuel cells by serigraphically printing cathode catalysts (3) or anode catalysts (6) with a carbon baking layer (4, 7) onto graphite or carbon paper (5, 8), boiling impurities from these layers, and bonding the boiled, printed cathode and anode catalyst layers onto opposite sides of a polymer electrolyte membrane (2) via semi-isostatic compression in a constraint which restricts volume and lateral deformation is provided. Also provided are membrane electrode assemblies produced in accordance with this method.

WO 02/039533 A3

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/13135

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01M8/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01M B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, INSPEC, COMPENDEX, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A P,A	WO 99 66578 A (OHARA HIDEO ;ONO YUKIYOSHI (JP); SAKAI OSAMU (JP); UCHIDA MAKOTO () 23 December 1999 (1999-12-23) -& EP 1 096 587 A (MATSUSHITA ELECTRIC INDUSTRIAL CO LTD) 2 May 2001 (2001-05-02) column 7, line 32 - line 40 column 14, line 3 - line 49 examples 5,7	1,2
A	PATENT ABSTRACTS OF JAPAN vol. 014, no. 065 (E-0884), 6 February 1990 (1990-02-06) -& JP 01 286256 A (MATSUSHITA ELECTRIC IND CO LTD), 17 November 1989 (1989-11-17) abstract --- -/-	1,2



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

9 December 2002

Date of mailing of the international search report

16/12/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Gamez, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 01/13135

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A P,A	WO 00 11741 A (OHARA HIDEO ;ONO YUKIYOSHI (JP); SAKAI OSAMU (JP); UCHIDA MAKOTO () 2 March 2000 (2000-03-02) -& EP 1 117 142 A (MATSUSHITA ELECTRONICS CORPORATION) 18 July 2001 (2001-07-18) column 3, line 24 - line 37 example 1 -----	1,2
A	CHRISTENSEN H ET AL: "REQUIREMENTS FOR MASS PRODUCTION OF SOFC-COMPONENTS" PROCEEDINGS OF THE INTERNATIONAL SYMPOSIUM ON SOLID OXIDE FUEL CELLS. ATHENS, JULY 2 - 5, 1991, LUXEMBURG, EEC, LU, vol. SYMP. 2, 2 July 1991 (1991-07-02), pages 839-844, XP000546180 ISBN: 92-826-2556-7 page 841, paragraph 4 - paragraph 6 -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 01/13135

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9966578	A	23-12-1999	JP 2000003714 A	07-01-2000
			JP 2000123842 A	28-04-2000
			JP 2000228204 A	15-08-2000
			JP 2000243404 A	08-09-2000
			CN 1305647 T	25-07-2001
			EP 1096587 A1	02-05-2001
			WO 9966578 A1	23-12-1999
<hr/>				
JP 01286256	A	17-11-1989	NONE	
<hr/>				
WO 0011741	A	02-03-2000	JP 2000067874 A	03-03-2000
			JP 2000228205 A	15-08-2000
			CN 1314010 T	19-09-2001
			EP 1117142 A1	18-07-2001
			WO 0011741 A1	02-03-2000
<hr/>				